



# TECHNICAL DATA SHEET

## P004 - GR16

POLYESTER POLYURETHANE POWDER COATING  
SEMI GLOSS SMOOTH  
ANSI #61 GRAY

LS #:

RoHS Compliant

### POWDER PROPERTIES

SPECIFIC GRAVITY: 1.69 CALCULATED  
 COVERAGE: 56.89 SQ.FT./LB. @ 2 MILS (100% EFFICIENCY)  
 PARTICLE SIZE: 25 - 75 MICRONS AVERAGE  
 STORAGE; STORE BELOW 80 DEGREES F, IN COOL DRY ENVIRONMENT  
 SHELF LIFE: MINIMUM OF 1 YEAR  
 CURE SCHEDULE: (METAL TEMPERATURE) 12 MINUTES @ 400 DEGREES F.

### CURED FILM PROPERTIES

ALL TESTS WERE PERFORMED AT A FILM THICKNESS OF: 2.0 to 3.5 mils

TEST	METHOD	RANGE
GLOSS @ 60 DEGREES:	D523	35 +/-10
DIRECT IMPACT (INCH LBS.):	D2794	100 in.lbs
INDIRECT IMPACT (INCH LBS.):	D2794	100 in.lbs
PENCIL HARDNESS:	D3363	2H
CROSS HATCH ADHESION:	D3359B	4B
FLEXIBILITY (CONICAL MANDREL):	D1737/D522	100%

### CHEMICAL AND CORROSION EXPOSURE TESTS

CHEMICAL RESISTANCE: Good to excellent resistance to most solvents, oils, acids, and alkalis.  
 OVERBAKE RESISTANCE: Slight yellowing is evident, especially in white and pastel colors.

All tests were performed on 24 gauge Bonderite 1000 panels

### APPLICATION

This product was designed to be applied by electrostatic spray, on steel, galvanized steel, or aluminum. Most powders can be reclaimed, sieved and recycled, if proper housekeeping is maintained.

### PRE TREATMENT

The substrate pretreatment prior to powder coating is a critical factor in developing maximum corrosion resistance and maximizing the lifetime of the product.

C.R.S. (Iron phosphate): 2 to 5 stages depending upon soil level, and quality desired.  
 C.R.S. (Zinc phosphate): 5 to 9 stages depending upon soil level, and quality desired.  
 Galvanized steel (Zinc phosphate): 5 to 7 stages depending on soil level, and quality desired.  
 Galvanized steel must be degassed at 5 degrees above cure temperature to minimize gassing.  
 Aluminum (Chromate): 5 stage system is normally needed.  
 Aluminum (phosphate): 5 stage system is normally needed.

L14MS

**IMPORTANT: Warranty and Disclaimer** – The performance characteristics of these products vary according to the product application, operating conditions, materials applied to or use. Since these factors can affect results, we strongly recommend that you make your own tests to determine your satisfaction whether the product is of acceptable quality, has not been affected by storage or transportation and is suitable for your particular purpose under your own operating conditions prior to using any product in full scale production. Seller warrants the products to be free from defects in materials and workmanship. SUCH WARRANTY IS EXCLUSIVE AND IS IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE. No representative of ours has authority to waive or change this provision, which applies to all sales of these products.

[www.cardinalpaint.com](http://www.cardinalpaint.com)

<b>Southern California</b> Corporate Headquarters 1329 Potrero Avenue South El Monte, CA 91733 tel 626.444.9274 fax 626.444.0382	<b>Powder Coating</b> <b>Manufacturing</b> tel 626.937.6767	<b>Arizona</b> tel 602.437.2401	<b>Colorado</b> tel 303.286.1876	<b>Missouri</b> tel 314.878.3010	<b>Pennsylvania</b> tel 814.728.0721	<b>Washington State</b> tel 425.483.5665
		<b>Northern California</b> tel 408.452.8522	<b>Minnesota</b> tel 952.469.6021	<b>North Carolina</b> tel 336.882.9493	<b>Texas</b> tel 214.333.9801	<b>Hong Kong</b> tel 852.2410.8200